

(19)



Europäisches Patentamt

Europ an Patent Office

Offic européen de brevets



(11)

EP 1 249 484 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
16.10.2002 Bulletin 2002/42(51) Int Cl.7: C09K 19/58, C07C 69/76,
C07C 69/82, C07C 69/90

(21) Application number: 02008128.7

(22) Date of filing: 11.04.2002

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 13.04.2001 JP 2001115602
25.04.2001 JP 2001126990(71) Applicant: MITSUBISHI GAS CHEMICAL
COMPANY, INC.
Tokyo 100-0005 (JP)


(72) Inventors:

- Norisue, Yasumasa, Tokyo Factory
Katsushika-ku, Tokyo 125-0051 (JP)
- Mine, Takakiyo, Tokyo Factory
Katsushika-ku, Tokyo 125-0051 (JP)
- Johno, Masahiro, Tokyo Factory
Katsushika-ku, Tokyo 125-0051 (JP)

(74) Representative: Albrecht, Thomas, Dr. et al
Kraus & Weisert,
Thomas-Wimmer-Ring 15
80539 München (DE)

(54) Optically active compound and liquid crystal composition containing the compound

(57) An optically active compound of the following general formula (1) useful as a chiral dopant, and use thereof,



wherein each of X and Y is independently a hydrogen atom or a fluorine atom, R is (C₂H₅)₂CHCH₂C^{*}H(CH₃)- or Ph-C^{*}H(CH₃)-, A is -Ph(W)-COO-Ph-, -Ph-Ph-COO-, -Cy-COO-Ph-, -Ph(W)-OOC-Ph-COO-, -Ph(W)-OOC-Cy-COO-, -Ph(W)-OOC-Np-COO- or -Np-OOC-, in which Ph- is a phenyl group, -Ph- is a 1,4-phenylene group, -Ph(W)- is -Ph- or monofluoro substituted -Ph-, Cy- is a trans-1,4-cyclohexylene group and -Np- is a 2,6-naphthylene group, and C^{*} is an asymmetric carbon.

The optically active compound of the present invention has a large helical twisting power (HTP) of at least 14 and suitably has the property that its induced helical pitch decreases in length with an increase in temperature, so that it has an excellent value as a chiral dopant for a nematic liquid crystal composition.

EP 1 249 484 A1

Description

Detailed Description of the Invention

5 Field of Industrial Utilization

[0001] The present invention relates to a novel optically active compound useful as a chiral dopant, a liquid crystal composition containing the compound and a liquid crystal display device to which the liquid crystal composition is applied. More specifically, it relates to a chiral dopant having a helical twisting power (HTP) of at least 14 and having the property that a helical pitch induced decreases with an increase in temperature, and use thereof.

Prior Art

[0002] Various modes are known as display modes of liquid crystal display devices, and in most of such display modes, it is required to control the helical pitch of a liquid crystal. The mode that requires control of the helical pitch of a liquid crystal includes the following modes.

[0003] The modes that have been put to practical use and widely employed are a twisted nematic mode (TN mode) and a super twisted nematic mode (STN mode) using a nematic liquid crystal.

[0004] In the TN mode, liquid crystal molecules are aligned so as to twist at 90 degrees between an upper substrate and a lower substrate, and a 1/4 pitch of a helix is formed in a cell.

[0005] In the STN mode, liquid crystal molecules are aligned so as to twist at approximately 220 degrees between an upper substrate and a lower substrate, and an approximately 3/5 pitch of a helix is formed in a cell.

[0006] The TN mode is employed in a simple matrix driving liquid crystal display device and an active matrix driving liquid crystal display device, and the STN mode is employed in a simple matrix driving liquid crystal display device.

Brief Description of Drawings

[0007]

Fig. 1 schematically shows a planar alignment of a chiral nematic liquid crystal.

Fig. 2 schematically shows a focal-conic alignment of a chiral nematic liquid crystal.


[0008] As another mode in addition to the above TN mode and STN mode, there is a selective reflection (SR) mode of a chiral nematic liquid crystal. As shown in Figs. 1 and 2, in the SR mode, a liquid crystal has a planar molecule alignment state (Fig. 1) in which helical axes are perpendicular to substrates and a focal-conic molecule alignment state (Fig. 2) in which directions of helical axes are at random. These two states are switched with voltage pulse. In the planar molecule alignment state, light having a wavelength corresponding to a helical pitch is reflected, and in the focal-conic molecule alignment state, light is transmitted through a device. When a reflection state is used as "bright" and when a transmission state is used as "dark", a display is made possible.



[0009] In the present specification, "nematic liquid crystal" refers to a nematic liquid crystal that does not contain the chiral dopant of the present invention. Further, "liquid crystal composition" or "nematic liquid crystal composition" refers to a nematic liquid crystal composition containing the chiral dopant of the present invention. Further, "liquid crystal" refers to a composition containing a mixture of a plurality of liquid crystal compounds unless it is specified to be any specific compound, and the "liquid crystal" will be sometimes referred to as "base liquid crystal". Further, "chiral dopant" refers to an optically active compound that induces a helical structure or a mixture of such compounds.

[0010] As is already described, an optically active compound that induces a helical structure is generally called "chiral dopant". Many chiral dopants have been synthesized, and typical compounds thereof are compounds having the following structures.

Name Structural formula

[0011]





[0012] The most essential performance that is required of a chiral dopant compound is to have large helical twisting power. The helical twisting power (HTP) refers to a physical quantity defined by the following expression.

$$\text{HTP } (\mu\text{m}^{-1}) = 1/(\text{amount of chiral dopant added} \\ (\text{wt\%})/100 \times \text{induced helical pitch } (\mu\text{m}))$$

[0013] Generally, chiral dopants themselves exhibit no liquid crystallinity, and most of them have large molecular weights. When a large amount of a chiral dopant is added to a base liquid crystal, it degrades various performances in many cases. The degradation of the performances includes a decrease in temperature for phase transition from an isotropic phase to a nematic phase, an increase in viscosity of a liquid crystal and an easy occurrence of crystallization. A chiral dopant having large helical twisting power serves to prevent the degradation of the performances since a desired helical pitch can be obtained by adding a small amount of such a chiral dopant to the base liquid crystal.

[0014] In addition to the above problems, the SR mode further has a problem that the helical pitch depends upon temperatures. That is, in the SR mode, a liquid crystal reflects (selectively reflects) light corresponding to a helical pitch to produce a bright state. However, when chiral dopants that have been already developed are used, the helical pitch increases in length with an increase in temperature, so that there is caused a problem that reflected light changes in color.

[0015] A change in wavelength of selectively reflected light with an increase in temperature is referred to as "wavelength shift". An increase in wavelength of selectively reflected light caused by an increase in temperature is defined to be plus wavelength shift, and a decrease in wavelength of selectively reflected light is defined to be minus wavelength shift.


[0016] For removing the dependency of wavelength of selectively reflected light upon temperatures, it has been attempted to combine a chiral dopant that shows a plus wavelength shift and a chiral dopant that shows a minus wavelength shift. However, there are very few chiral dopants that show a minus wavelength shift, and there are reported only four chiral dopants having a helical twisting power (HTP) of at least 9, which are disclosed in U.S. Patent 6217792, JP-A-62-195347 and JP-A-2-053768. Those compounds that have been so far disclosed are not satisfactory, since these compounds exhibit small shift amounts and have a problem that they are liable to cause crystallization even when added in a small amount.

Problems to be Solved by the Invention

[0017] It is an object of the present invention to provide a chiral dopant that has large helical twisting power (HTP) and has a characteristic feature that the helical pitch induced decreases in length with an increase in temperature (has a minus wavelength shift).

Means to Solve the Problems

[0018] According to the present invention, there is provided an optically active compounds of the following general formula (1) useful as a chiral dopant.



wherein each of X and Y is independently a hydrogen atom or a fluorine atom, R is $(\text{C}_2\text{H}_5)_2\text{CHCH}_2\text{C}^*\text{H}(\text{CH}_3)$ - or $\text{Ph-C}^*\text{H}(\text{CH}_3)$ -, A is -Ph(W)-COO-Ph-, -Ph-Ph-COO-, -Cy-COO-Ph-, -Ph(W)-OOC-Ph-COO-, -Ph(W)-OOC-Cy-COO-, -Ph(W)-OOC-Np-COO- or -Np-OOC-, in which Ph- is a phenyl group, -Ph- is a 1,4-phenylene group, -Ph(W)- is -Ph- or monofluoro substituted -Ph-, Cy- is a trans-1,4-cyclohexylene group and -Np- is a 2,6-naphthylene group, and C* is an asymmetric carbon.

[0019] The optically active compound of the above general formula (1) has excellent properties as a chiral dopant. The optically active compound of the present invention is accordingly used as an additive to nematic liquid crystals. That is, the optically active compound is used as a component for a nematic liquid crystal composition containing at least one compound thereof.

[0020] The nematic liquid crystal composition is held between substrates having electrodes and used for liquid crystal display devices.

[0021] In the above general formula (1), each of X and Y is independently a hydrogen atom or a fluorine atom, and preferably, both of X and Y are hydrogen atoms. Further, -Ph(W)- of -A- is preferably -Ph-(1,4-phenylene group), and -A- is preferably -Ph(W)-COO-Ph-. The optically active compounds of the above general formula (1) advantageously have a helical twisting power (HTP) of at least 14, and more advantageously, at least 16. And, preferably, the above optically active compounds have the property that the induced helical pitch decreases with an increase in temperature.

[0022] The optically active compounds of the present invention have two optically active carbons on left and right hand sides, one each as shown in the general formula (1). The optically active compounds therefore include four optical isomers of R-R, R-S, S-R and S-S configurations.

[0023] Of the above optical isomers, the R-R and S-S configuration isomers have excellent properties as chiral dopants. The R-R configuration isomer and the S-S configuration isomer differ from each other in twisting direction (right-twisting or left-twisting) of the helical pitch induced. When the compounds of the general formula (1) are used, compounds are therefore selected therefrom by taking account of the twisting direction of a chiral dopant to be used in combination.

[0024] Further, when a large amount of a single compound from the optically active compounds of the present invention is added to a nematic liquid crystal as a base liquid crystal, the resultant composition having some combination may undergo crystallization at room temperature. In this case, however, the crystallization can be easily avoided by using other chiral dopant in combination.

[0025] When the optically active compound(s) of the present invention is/are used as chiral dopant(s), the amount of the optically active compound(s) based on the nematic liquid crystal to which the optically active compound(s) is/are added, is generally in the range of from 1 to 30 % by weight, preferably 1 to 20 % by weight. The above amount ratio is determined to be in the above preferred range on the basis of values of helical twisting power (HTP) and crystallinity of the optically active compound(s) and types of a nematic liquid crystal.

Effect of the Invention

[0026] According to the present invention, there is provided a chiral dopant that has a large helical twisting power (HTP) and has the characteristic feature that the induced helical pitch decreases in length with an increase in temperature. In liquid crystals for use in TN mode or STN mode, therefore, the helical pitch can be adjusted only by adding a small amount of the chiral dopant of the present invention, so that the degradation of performances of a base liquid crystal can be suppressed. In a liquid crystal operated in SR mode, a chiral dopant that induces a plus wavelength shift and the optically active compound(s) of the present invention are used in combination, whereby there can be obtained a liquid crystal composition free of a change that occurs in helical pitch depending upon temperatures.

Examples

[0027] The present invention will be further specifically explained with reference to Examples and Comparative Ex-

amples, while the present invention naturally shall not be limited thereto.

Example 1

5 (Formula (1): Each of X and Y is H, A is -Ph-COO-Ph-, and R is $(C_2H_5)_2CHCH_2C^*H(CH_3)$ - (E1))

Preparation of 4'-((R)-3-ethyl-1-methylpentyloxycarbonyl)biphenyl-4'-((R)-3-ethyl-1-methylpentyloxycarbonyl)benzoate;

10 (1) Synthesis of 4'-acetoxybiphenyl-4-carboxylic acid

[0028] 50 Grams (234 mmol) of 4'-hydroxybiphenyl-4-carboxylic acid and 238 g (2.34 mol) of acetic anhydride were placed in a reactor, and while these stirred, 0.1 g of concentrated sulfuric acid was added. The mixture was stirred until heat generation ceased, and the mixture was further heated at 80°C for 4 hours with stirring and then gradually cooled to room temperature. While the reaction mixture was cooled in an ice bath, 500 g of water was gradually added, and the mixture was stirred at room temperature for 3 hours to quench unreacted acetic anhydride. A precipitated white solid was recovered by filtration, washed with water to remove acetic acid, and dried with a vacuum drier to give 59.8 g of an end compound (yield 99 %).

20 (2) Synthesis of 4'-acetoxybiphenyl-4-carbonyl chloride

[0029] 59.8 g (233.4 mmol) of 4'-acetoxybiphenyl-4-carboxylic acid and 278 g (2.33 mol) of purified thionyl chloride were placed in a reactor and refluxed under heat (79°C) for 4 hours. Thionyl chloride was distilled off under atmospheric pressure, 150 ml of toluene was added, and toluene and thionyl chloride were distilled off under reduced pressure, to give 63 g of an end compound (yield 98 %).

(3) Synthesis of (R)-3-ethyl-1-methylpentyl-4'-acetoxybiphenyl-4-carboxylate

[0030] 18.6 Grams (67.6 mmol) of 4'-acetoxybiphenyl-4-carbonyl chloride, 8.0 g (61.4 mmol) of (R)-4-ethyl-2-hexanol and 140 ml of toluene were placed in a reactor, 9.7 g (122.9 mmol) of pyridine was dropwise added thereto, and the mixture was stirred at room temperature for 3 hours. To the reaction solution was added 40 ml of water, the mixture was stirred at room temperature for 30 minutes, and a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water, and the washed organic layer was dried over anhydrous sodium sulfate and filtered, and the solvent was distilled off to give 22 g of an end compound (yield 99 %).

(4) Synthesis of (R)-3-ethyl-1-methylpentyl-4'-hydroxybiphenyl-4-carboxylate

[0031] 22 Grams (59.7 mmol) of (R)-3-ethyl-1-methylpentyl-4'-acetoxybiphenyl-4-carboxylate and 390 ml of toluene was placed in a reactor, a solution of 40 % methylamine in methanol was dropwise added thereto, and the mixture was stirred at room temperature for 3 hours. The reaction solution was washed with 2N hydrochloric acid and with water to separate the mixture into two layers of liquid, an organic layer was dried over anhydrous sodium sulfate and filtered, and the solvent was distilled off to give 19 g of an end compound (yield 97 %).

45 (5) Synthesis of 4'-((R)-3-ethyl-1-ethylpentyloxycarbonyl)biphenyl-4'-((R)-3-ethyl-1-ethylpentyloxycarbonyl)benzoate

[0032] 2.0 Grams (6.12 mmol) of (R)-3-ethyl-1-methylpentyl-4'-hydroxybiphenyl-4-carboxylate, 1.8 g (8.86 mmol) of terephthaloyl dichloride and 150 ml of anhydrous dichloromethane were placed in a reactor, 3 g (37 mmol) of pyridine was dropwise added thereto, and the mixture was stirred at room temperature for 6 hours. To the reaction mixture was added 1.5 g (11.5 mmol) of (R)-4-ethyl-2-hexanol, and the mixture was stirred at room temperature for 18 hours. To the reaction solution was added 50 ml of water, the mixture was stirred at room temperature for 2 hours, and then a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and washed with water. The washed organic layer was dried over anhydrous sodium sulfate and filtered, and then the solvent was distilled off. The thus-obtained crude product was purified by silica gel chromatography, to give 1.2 g (2.04 mmol, yield 23 %) of an end compound.

Example 2

(Formula (1): each of X and Y is H, A is -Ph-COO-Ph-, and R is Ph-C*H(CH₃)- (E2))

5 Preparation of 4-((R)-3-ethyl-1-methylpentylloxycarbonyl)biphenyl-4'-((R)-α-methylbenzylloxycarbonyl)benzoate;

[0033] An end compound was obtained in the same manner as in Example 1 except that (R)-4-ethyl-2-hexanol in (5) of Example 1 was replaced with (R)-1-phenylethanol (11.5 mmol).

10 Example 3

(Formula (1): Each of X and Y is H, A is -Cy-COO-Ph- and R is Ph-C*H(CH₃)- (E3))

15 Preparation of 4-((R)-3-ethyl-1-methylpentylloxycarbonyl)biphenyl-4'-(4-trans-((R)-α-methylbenzylloxycarbonyl)cyclohexyl)-carboxylate;

[0034] 12.5 Grams (12.5 mmol) of 1,4-trans-cyclohexyldicarboxylic acid, 3.1 g (15 mmol) of dicyclohexylcarbodiimide and 220 ml of dehydrated dichloromethane were placed in a reactor and stirred. Then, 1.22 g (10 mmol) of (R)-1-phenylethanol and 0.31 g (2.5 mmol) of 4-dimethylaminopyridine were added, and the mixture was stirred at room temperature for 6 hours. To this reaction mixture was added 4.9 g (15 mmol) of (R)-3-ethyl-1-methylpentyl-4'-hydroxybiphenyl-4-carboxylate that had been obtained in the same manner as in (4) of Example 1, and the mixture was stirred at room temperature for 48 hours.

[0035] To the reaction solution was added 20 ml of water, and the mixture was stirred at room temperature for 1 hour. Then, insolubles were separated by filtration, and diethyl ether was added, to separate the mixture into two organic layers of liquid. The obtained organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and washed with water, and the washed organic layer was dried over anhydrous sodium sulfate and filtered. The filtrate was distilled to remove the solvent.

[0036] The thus-obtained crude product was purified by silica gel chromatography and recrystallized from hexane to give 0.62 g (1.1 mmol, yield 11 %) of an end compound.

30 Example 4

(Formula (1): Each of X and Y is H, A is -Ph-Ph-COO- and R is (C₂H₅)₂CHCH₂C*H(CH₃)- (E4))

35 Preparation of 4-((R)-3-ethyl-1-methylpentylloxycarbonyl)phenyl-4'-((R)-3-ethyl-1-methylpentylloxycarbonyl)-4-biphenylcarboxylate;

(1) Synthesis of 4-acetoxybenzoyl chloride

40 [0037] 100 Grams (0.555 mol) of 4-acetoxybenzoic acid was added to 400 g (3.36mol) of thionyl chloride, and the mixture was refluxed under heat for 4 hours.

[0038] Then, excess thionyl chloride was distilled off, and then the remainder was purified by distillation under reduced pressure (4 mmHg, 116°C), to give 99 g (0.498 mol, yield 90 %) of an end compound.

45 (2) Synthesis of (R)-4-acetoxy-1-(3-ethyl-1-methylpentylloxycarbonyl)benzene

[0039] 49 Grams (0.246 mol) of 4-acetoxybenzoyl chloride, 29 g (0.222 mol) of (R)-4-ethyl-2-hexanol and 750 ml of dehydrated toluene were placed in a reactor, 35 g (0.442 mol) of pyridine was dropwise added thereto, and the mixture was stirred at room temperature for 15 hours.

50 [0040] To the reaction solution was added 300 ml of water, and the mixture was stirred at room temperature for 1 hour, followed by separating of the reaction mixture into two organic layers of liquid. The obtained organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water. The washed organic layer was dried over anhydrous sodium sulfate and filtered, and the solvent was removed from the filtrate by distillation, to give 63 g (0.215 mol, yield 97 %) of an end compound.

55 (3) Synthesis of (R)-4-hydroxy-1-(3-ethyl-1-methylpentylloxycarbonyl)benzene

[0041] 63 Grams (0.215 mol) of (R)-4-acetoxy-1-(3-ethyl-1-methylpentylloxycarbonyl)benzene was dissolved in 900

ml of dehydrated toluene, 25 g of a solution of 40 % methylamine in methanol was dropwise added, and the mixture was stirred at room temperature for 5 hours. The reaction mixture was washed with 2N hydrochloric acid and washed with water. The resultant organic layer was dried over anhydrous sodium sulfate and filtered, and then the solvent was distilled off, to give 49 g (0.195 mol, yield 91 %) of an end compound.

(4) Synthesis of 4-((R)-3-ethyl-1-methylpentyloxycarbonyl)phenyl-4'-((R)-3-ethyl-1-methylpentyloxycarbonyl)-4-biphenylcarboxylate

[0042] 3.1 Grams (12.3 mmol) of (R)-4-hydroxy-1-(3-ethyl-1-methylpentyloxycarbonyl)benzene, 3.1 g (11.1 mmol) of 4,4'-biphenyldicarbonyl chloride and 100 ml of dehydrated dichloromethane were placed in a reactor, 4 g (48 mmol) of pyridine was dropwise added, and the mixture was stirred at room temperature for 6 hours. Further, 1.5 Grams (11.5 mmol) of (R)-4-ethyl-2-hexanol was added, and the mixture was stirred at room temperature for 18 hours. To the reaction solution was added 50 ml of water, and the mixture was stirred at room temperature for 2 hours. Then, a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water, the washed organic layer was dried over anhydrous sodium sulfate and filtered, and then the solvent was distilled off. The thus-obtained crude product was purified by silica gel chromatography, to give 2.0 g (3.40 mmol, yield 30 %) of an end compound.

Example 5

(Formula (1): X is H, Y is F, A is -Ph-Ph-COO-, and R is $(C_2H_5)_2CHCH_2C^*H(CH_3)$ - (E5))

Preparation of 3-fluoro-4-((R)-3-ethyl-1-methylpentyloxycarbonyl)phenyl-4'-((R)-3-ethyl-1-methylpentyloxycarbonyl)-4-biphenylcarboxylate;

[0043] An end compound was obtained in the same manner as in Example 4 except that 4-acetoxybenzoic acid in (1) of Example 4 was replaced with 4-acetoxy-2-fluorobenzoic acid (0.555 mol).

Example 6

(Formula (1): Each of X and Y is H, A is -Ph-Ph-COO- and R is $Ph-C^*H(CH_3)$ - (E6))

Preparation of 4-((R)- α -methylbenzyloxycarbonyl)phenyl-4'-((R)-3-ethyl-1-methylpentyloxycarbonyl)-4-biphenylcarboxylate;

[0044] 2.02 Grams (16.5 mmol) of (R)-phenylethanol, 3.75 g (15 mmol) of 4,4'-biphenyldicarbonyl chloride and 100 ml of dehydrated dichloromethane were placed in a reactor, 3.6 g (45 mmol) of pyridine was dropwise added, and the mixture was stirred at room temperature for 6 hours. Further, 4.6 g (16.5 mmol) of (R)-4-hydroxy-1-(3-ethyl-1-methylpentyloxycarbonyl)benzene obtained in the same manner as in (3) of Example 4 was added thereto, 3.6 g (45 mmol) of pyridine was dropwise added, and the mixture was stirred at room temperature for 48 hours. To the reaction solution was added 50 ml of water, the mixture was stirred at room temperature for 2 hours, and then a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water, the washed organic layer was dried over anhydrous sodium sulfate and filtered, and then the solvent was distilled off. The thus-obtained crude product was purified by silica gel chromatography, to give 1.6 g (2.7 mmol, yield 17 %) of an end compound.

Example 7

(Formula (1): Each of X and Y is H, A is -Ph-OOC-Ph-COO- and R is $(C_2H_5)_2CHCH_2C^*H(CH_3)$ - (E7))

Preparation of 1,4-di-[4-((R)-3-ethyl-1-methylpentyloxycarbonyl)phenyloxycarbonyl]benzene;

[0045] 3.0 Grams (11.9 mmol) of (R)-4-hydroxy-1-(3-ethyl-1-methylpentyloxycarbonyl)benzene obtained in the same manner as in (3) of Example 4, 1.0 g (4.92 mmol) of terephthaloyl dichloride and 50 ml of dehydrated toluene were placed in a reactor, 2 g (24 mmol) of pyridine was dropwise added, and the mixture was stirred at room temperature for 15 hours. To the reaction solution was added 30 ml of water, the mixture was stirred at room temperature for 2 hours, and a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water, the washed organic layer was dried over

EP 1 249 484 A1

anhydrous sodium sulfate and filtered, and then the solvent was distilled off. The thus-obtained crude product was purified by silica gel chromatography, to give 2.2 g (3.48 mmol, yield 70 %) of an end compound.

Example 8

(Formula (1): X is H, Y is F, A is -Ph(F)-OOC-Ph-COO-, and R is (C₂H₅)₂CHCH₂C*H(CH₃)- (E8))

Preparation of 1,4-di-[3-fluoro-4-((R)-3-ethyl-1-methylpentylloxycarbonyl)phenylloxycarbonyl]benzene;

[0046] An end compound was obtained in the same manner as in Example 7 except that (R)-4-hydroxy-1-(3-ethyl-1-methylpentylloxycarbonyl)benzene was replaced with (R)-4-hydroxy-2-fluoro-1-(3-ethyl-1-methylpentylloxycarbonyl)benzene (11.9 mmol).

Example 9

(Formula (1): Each of X and Y is H, A is -Ph-OOC-Np-COO-, and R is (C₂H₅)₂CHCH₂C*H(CH₃)- (E9))

Preparation of 2,6-di-[4-((R)-3-ethyl-1-methylpentylloxycarbonyl)phenylloxycarbonyl]naphthalene

[0047] 2.6 Grams (10.3 mmol) of (R)-4-hydroxy-1-(3-ethyl-1-methylpentylloxycarbonyl)benzene obtained in the same manner as in (3) of Example 4, 1.0 g (4.92 mmol) of 2,6-naphthalenedicarboxylic acid and 50 ml of dehydrated dichloromethane were placed in a reactor, 2.3 g (11.1 mmol) of dicyclohexylcarbodiimide and 0.26 g (2.1 mmol) of 4-dimethylaminopyridine were added, and the mixture was stirred at room temperature for 24 hours. To the reaction solution was added 20 ml of water, and the mixture was stirred at room temperature for 1 hour. Then, the reaction mixture was filtered with Celite, and diethyl ether was added to separate a liquid of an organic layer. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water. The washed organic layer was dried over anhydrous sodium sulfate and filtered, and the solvent was distilled off. The thus-obtained crude product was purified by silica gel chromatography, to give 2.0 g (2.93 mmol, yield 59 %) of an end compound.

Example 10

(Formula (1): Each of X and Y is H, A is -Ph-OOC-Cy-COO-, and R is (C₂H₅)₂CHCH₂C*H(CH₃)- (E10))

Preparation of 1,4-trans-di-[4-((R)-3-ethyl-1-methylpentylloxycarbonyl)phenylloxycarbonyl]cyclohexane

[0048] An end compound was obtained in the same manner as in Example 9 except that 2,6-naphthalenedicarboxylic acid was replaced with 1,4-trans-cyclohexyldicarboxylic acid (4.92 mmol).

Example 11

(Formula (1): Each of X and Y is H, A is -Np-OOC-, and R is Ph-C*H(CH₃)- (E11))

Preparation of 6-((R)-α-methylbenzylloxycarbonyl)naphthyl-2-((R)-3-ethyl-1-methylpentylloxycarbonyl)benzoate

(1) Synthesis of 6-acetoxy-2-naphthoic acid

[0049] 25 Grams (133 mmol) of 6-hydroxy-2-naphthoic acid and 68 g (265 mmol) of acetic anhydride were placed in a reactor, and while the mixture was stirred, 0.05 g of concentrated sulfuric acid was added. The mixture was stirred until heat generation ceased, and the mixture was further heated and stirred at 80°C for 1 hour and then gradually cooled to room temperature. While the reaction mixture was cooled in an ice bath, 500 g of water was gradually added, and the mixture was stirred at room temperature for 3 hours to quench unreacted acetic anhydride. A precipitated white solid was recovered by filtration, washed with water to remove acetic acid, and dried with a vacuum dryer, to give 30.3 g of an end compound (yield 99 %)

(2) Synthesis of 6-acetoxy-2-naphthoyl chloride

[0050] 30 Grams (130.3 mmol) of 6-acetoxy-2-naphthoic acid and 155 g (260 mmol) of purified thionyl chloride were

placed in a reactor, and the mixture was refluxed under heat (79°C) for 4 hours. Thionyl chloride was distilled off under atmospheric pressure, 150 ml of toluene was added, and toluene and thionyl chloride were distilled off under reduced pressure, to give 33 g of an end compound (yield 98 %).

(3) Synthesis of (R)- α -methylbenzyl-6-acetoxynaphthyl-2-carboxylate

[0051] 11.2 Grams (45 mmol) of 6-acetoxy-2-naphthoyl chloride, 5.0 g (45 mmol) of (R)-phenylethanol and 88 ml of toluene were placed in a reactor, 6.5 g (90 mmol) of pyridine was dropwise added thereto, and the mixture was stirred at room temperature for 3 hours. To the reaction solution was added 20 ml of water, the mixture was stirred at room temperature for 30 minutes, and then a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water. The washed organic layer was dried over anhydrous sodium sulfate and filtered, and the solvent was distilled off, to give 10.7 g of an end compound (yield 78 %).

(4) Synthesis of (R)- α -methylbenzyl-6-hydroxynaphthyl-2-carboxylate

[0052] 10.7 Grams (32.2 mmol) of (R)- α -methylbenzyl-6-acetoxynaphthyl-2-carboxylate and 185 ml of toluene were placed in a reactor, a solution of 40 % methylamine in methanol was dropwise added thereto, and the mixture was stirred at room temperature for 3 hours. The reaction solution was washed with 2N hydrochloric acid and water to separate the mixture to two layers of liquid. The organic layer was dried over anhydrous sodium sulfate and filtered, and then the solvent was distilled off, to give 8.9 g of an end compound (yield 95 %).


(5) Synthesis of 6-((R)- α -methylbenzyloxycarbonyl)naphthyl-2-((R)-3-ethyl-1-methylpentyloxycarbonyl)benzoate

[0053] 3.0 Grams (10.3 mmol) of (R)- α -methylbenzyl-6-hydroxynaphthyl-2-carboxylate, 2.5 g (20.5 mmol) of terephthaloyl dichloride and 104 ml of toluene were placed in a reactor, 1.6 g (20.5 mmol) of pyridine was dropwise added thereto, and the mixture was stirred at room temperature for 24 hours. Further, 1.87 g (14.4 mmol) of (R)-4-ethyl-2-hexanol and 1.6 g (20.5 mmol) of pyridine were added, and the mixture was stirred at room temperature for 24 hours. To the reaction solution was added 30 ml of water, the mixture was stirred at room temperature for 30 minutes, and a liquid of an organic layer was separated. The organic layer was washed with 2N hydrochloric acid, washed with a 1N sodium hydroxide aqueous solution and then washed with water, and dried over anhydrous sodium sulfate. The organic layer was filtered and then the solvent was distilled off. The thus-obtained crude product was purified by silica gel chromatography, to give 2.8 g (5 mmol, yield 48 %) of an end compound.


[0054] With regard to the optically active compounds (E1 to E11) obtained in the above Examples 1 to 11, results of $^1\text{H-NMR}$ thereof are shown in Tables 1 and 2, and a common portion in the general formula, R portions in the general formula and A portions in the general formula are respectively shown below.

[0055] Further, phase transition temperatures of the optically active compounds (E1 to E11) were determined by observation through a polarizing microscope and DSC measurement. The DSC measurement was conducted at a temperature decrease rate of 5°C/minute. Table 3 shows the results.

Common portion in general formula (1)



R portion in general formula (1)



A portion in general formula (1)




Table 1

Common portion in formula (1)				R portion in formula (1)			
No.	Benzene ring		Asymmetric carbon		Terminal methyl		
	1	2	3	4	5	6	7
E1	7.68	8.12	5.28	0.88	0.88	5.28	-
E2	7.68	8.11	5.27	0.88	7.33	7.40	7.48
E3	7.62	8.10	5.26	0.87	7.30	7.35	7.35
E4	7.31	8.14	5.27	0.88	0.88	5.27	-
E5	7.13	-	5.27	0.89	0.89	5.27	-
E6	7.31	8.29	5.26	0.87	7.39	7.31	7.47
E7	7.33	8.14	5.26	0.88	0.88	5.26	-
E8	7.14	-	5.27	0.88	0.88	5.27	-
E9	7.36	8.20	5.27	0.88	0.88	5.27	-
E10	7.25	8.07	5.23	0.86	0.86	5.23	-
E11	8.31	8.19	5.29	0.88	7.25	7.32	7.50
							6.21

Table 2

A portion in formula (1)						
No.	9	10	11	12	13	14
E1	8.28	8.19	7.33	7.68	-	-
E2	8.25	8.25	7.33	7.68	-	-

EP 1 249 484 A1

Table 2 (continued)

A portion in formula (1)						
No.	9	10	11	12	13	14
E3	2.38	←2.15 ~ 2.24→		2.55	7.16	7.62
E4	8.14	7.75	7.75	8.29	-	-
E5	8.15	7.22	7.77	8.03	-	-
E6	8.19	7.74	7.74	8.14	-	-
E7	8.14	7.33	8.35	8.35	-	-
E8	-	7.14	8.34	8.34	-	-
E9	8.20	7.36	8.20	8.20	8.87	-
E10	8.07	7.25	2.62	←1.72 ~ 2.30→		2.62
E11	8.67	7.88	7.41	8.14	8.04	7.76

Table 3

Compound	Phase sequence
E1	Iso (-40°C or lower) Cry
E2	Iso (-40°C or lower) Cry
E3	Iso (35) Cry
E4	Iso (35) Cry
E5	Iso (12) Cry
E6	Iso (-40°C or lower) Cry
E7	Iso (-40°C or lower) Cry
E8	Iso (36) Cry
E9	Iso (59) Cry
E10	Iso (44) Cry
E11	Iso (-40°C or lower) Cry

Notes) In Table, parenthesized values show phase transition temperatures (°C), Iso stands for an isotropic phase, and Cry stands for a crystal phase.

Example 12

[0056] The optically active compounds (E1 to E11) prepared above were measured for helical twisting powers (HTP) and wavelength shifts. To a nematic liquid crystal (ZLI-1565) supplied by Merck & Co., Inc., was added 10 % by weight, based on a resultant composition, of the optically active compound (E1) obtained from Example 1 to prepare a chiral nematic (N*) liquid crystal composition. The thus-prepared liquid crystal composition was measured for an upper limit temperature of its N* phase and selective reflection behaviors, and its helical twisting power (HTP) was determined on the basis of the selective reflection behaviors.

[0057] The upper-limit temperature of the N* phase was determined by observation through a polarizing microscope and DSC measurement. The selective reflection behaviors were measured according to the following procedures.

[0058] A liquid crystal cell with ITO electrodes (cell thickness 10 μm) was charged with the above liquid crystal composition in an isotropic state. The cell was adjusted to 60°C, a rectangular wave voltage of ±60 V was applied for approximately 1 minute, and the cell was rapidly cooled to room temperature to attain planar alignment. The above liquid crystal cell was evaluated for selective reflection behaviors at 25°C and 60°C with an automatic spectrophotometer. An HTP at 25°C was calculated on the basis of the following expressions.

$$\text{HTP } (\mu\text{m}^{-1}) = n/(\lambda_{25} \times C/100)$$

wherein n is a refractive index of the chiral nematic liquid crystal, λ₂₅ is a selective reflection wavelength (μm) at 25°C, and C is a concentration (wt%) of the chiral dopant. As a refractive index n, there was employed a value (1.6) that is the refractive index of ZLI-1565 as a base liquid crystal.

[0059] The wavelength shift was determined on the basis of the following expression.

$$\text{Wavelength shift (nm)} = \lambda_{60} - \lambda_{25}$$

wherein λ_{60} is a selective reflection wavelength (nm) at 60°C and λ_{25} is a selective reflection wavelength (nm) at 25°C. Table 4 summarizes the results.

[0060] It is seen that the optically active compound (E1) in Example 1 has an HTP of more than 14 and further has the property that the helix decreases in length with an increase in temperature.

Examples 13 to 22

[0061] The optically active compounds (E2 to E11) obtained in Examples 2 to 11 were measured for HTPs and wavelength shifts in the same manner as in Example 12. Incidentally, with regard to the compounds E10 and E11, 15 % by weight, based on a nematic liquid crystal composition, of each was added, and the compositions were measured. Further, since liquid crystal compositions containing E10 and E11 exhibited no selective reflection at 60°C, wavelength shifts (*1) between 25°C and 50°C were determined. Table 4 shows the results.

Comparative Examples 1 to 3

[0062] With regard to known optically active compounds CB15, S811 and CN shown in the explanation of Prior Art, nematic liquid crystal compositions were prepared in the same manner as in Example 12 except that CB15 and S811 were added in an amount of 15 % by weight based on the nematic liquid crystal composition each, and that CN was added in an amount of 30 % by weight based on the nematic liquid crystal composition, and the nematic liquid crystal compositions were measured for HTPs and wavelength shifts in the same manner as in Example 12. Table 4 also shows the results.


Table 4

Example	Compound	Iso-N* (°C)	HTP (1/μm)	Wavelength shift (nm)
12	E1	79	17.1	-101
13	E2	81	23.4	-81
14	E3	80	21.7	-59
15	E4	80	18.1	-72
16	E5	80	15.7	-93
17	E6	80	22.2	-59
18	E7	81	17.3	-78
19	E8	81	14.6	-78
20	E9	84	16.1	-136
21	E10	73	17.6	-43 (*1)
22	E11	70	22.7	-10 (*1)
C.Ex. 1	CB15	74	7.9	+193
C.Ex. 2	S811	73	10.1	+7
C.Ex. 3	CN	82	5.2	+34

Notes) In the table, C.Ex. = Comparative Example, and Iso-N* stands for a temperature of phase transition from an isotropic phase to a chiral nematic phase. (*1) shows that values are wavelength shifts between 25°C and 50°C.


Claims

1. An optically active compound of the following general formula (1),




wherein each of X and Y is independently a hydrogen atom or a fluorine atom, R is $(C_2H_5)_2CHCH_2C^*H(CH_3)-$ or $Ph-C^*H(CH_3)-$, A is $-Ph(W)-COO-Ph-$, $-Ph-Ph-COO-$, $-Cy-COO-Ph-$, $-Ph(W)-OOC-Ph-COO-$, $-Ph(W)-OOC-Cy-COO-$, $-Ph(W)-OOC-Np-COO-$ or $-Np-OOC-$, in which Ph- is a phenyl group, $-Ph-$ is a 1,4-phenylene group, $-Ph(W)-$ is $-Ph-$ or monofluoro substituted $-Ph-$, Cy- is a trans-1,4-cyclohexylene group and $-Np-$ is a 2,6-naphthylene group, and C^* is an asymmetric carbon.

2. The optically active compound of claim 1, which has the general formula (1) wherein X and Y are hydrogen atoms.
3. The optically active compound of claim 1, which has the general formula (1) wherein $-Ph(W)-$ is $-Ph-$.
4. The optically active compound of claim 1, which has the general formula (1) wherein A is $-Ph(W)-COO-Ph-$.
5. The optically active compound of claim 1, wherein the compound of the general formula (1) is the following compound.



6. The optically active compound of claim 1, wherein the compound of the general formula (1) is the following compound.



7. The optically active compound of claim 1, which has the general formula (1) wherein two asymmetric carbon atoms are R-configuration compounds together, or both S-configuration compounds together.
8. The optically active compound of claim 1, which has a helical twisting power (HTP) of at least 14.
9. The optically active compound of claim 1, which is characterized in that a helical pitch induced decreases in length with an increase in temperature.
10. A chiral dopant of the general formula (1).
11. A nematic liquid crystal composition containing at least one of optically active compounds of the general formula (1).
12. A liquid crystal display device having the nematic liquid crystal composition recited in claim 11 interposed between substrates having an electrode each.

FIG. 1





FIG. 2





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 02 00 8128

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	NAKAUCHI J ET AL: "FERROELECTRIC LIQUID CRYSTAL MIXTURES DOPED WITH COMPOUNDS HAVING CHIRAL GROUPS AT BOTH ENDS OF THE CORE" JAPANESE JOURNAL OF APPLIED PHYSICS, PUBLICATION OFFICE JAPANESE JOURNAL OF APPLIED PHYSICS. TOKYO, JP, vol. 28, no. 2, 1 February 1989 (1989-02-01), pages L272-274, XP000098738 ISSN: 0021-4922 * the whole document *	1-12	C09K19/58 C07C69/76 C07C69/82 C07C69/90
A	EP 0 528 268 A (BASF) 24 February 1993 (1993-02-24) * claims 1-12 *	1-12	
A	EP 0 517 504 A (MITSUBISHI GAS CHEMICAL) 9 December 1992 (1992-12-09) * claims *	1-12	
A	EP 0 449 049 A (HOFFMANN LA ROCHE) 2 October 1991 (1991-10-02) * claims *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C09K C07C
A	EP 0 405 346 A (HOFFMANN LA ROCHE ; NIOPIC MOSCOW RES & PROD ASS (SU)) 2 January 1991 (1991-01-02) * page 5, line 15 - line 56; claims *	1-12	
A	EP 0 329 153 A (DAINIPPON INK & CHEMICALS ; KAWAMURA INST CHEM RES (JP)) 23 August 1989 (1989-08-23) * claims *	1,2	
-/--			
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 June 2002	Examiner Serbetsoglou, A
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 (03.02.82) (P04201)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 00 8128

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 309 774 A (HOFFMANN LA ROCHE ; NIOPIC MOSCOW RES & PROD ASS (SU)) 5 April 1989 (1989-04-05) * claims 1-10 *	1-12	
A	EP 0 211 646 A (CHISSO CORP) 25 February 1987 (1987-02-25) * claims 1-15 *	1-12	
A	US 3 977 769 A (TSUKAMOTO MASAHI ET AL) 31 August 1976 (1976-08-31) * abstract * * column 2, line 55 - line 59 *	1	
A	EP 0 994 097 A (MITSUBISHI GAS CHEMICAL) 19 April 2000 (2000-04-19) * claims 1-7 *	1	
A	EP 0 937 765 A (MITSUBISHI GAS CHEMICAL) 25 August 1999 (1999-08-25) * claims 1,4 *	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Place of search THE HAGUE		Date of completion of the search 18 June 2002	Examiner Serbetsoglou, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 00 8128

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-06-2002

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0528268	A	24-02-1993	DE	4126996 A1	25-03-1993
			DE	59207831 D1	20-02-1997
			EP	0528268 A2	24-02-1993
			JP	5201926 A	10-08-1993
			US	5455325 A	03-10-1995
			US	5350873 A	27-09-1994
EP 0517504	A	09-12-1992	JP	3039571 B2	08-05-2000
			JP	5065486 A	19-03-1993
			DE	69213565 D1	17-10-1996
			DE	69213565 T2	06-03-1997
			EP	0517504 A1	09-12-1992
			US	5352382 A	04-10-1994
EP 0449049	A	02-10-1991	DE	59104009 D1	09-02-1995
			EP	0449049 A2	02-10-1991
			HK	49697 A	25-04-1997
			JP	2944244 B2	30-08-1999
			JP	4221346 A	11-08-1992
			KR	192730 B1	15-06-1999
			US	5230828 A	27-07-1993
EP 0405346	A	02-01-1991	DE	59009675 D1	26-10-1995
			EP	0405346 A2	02-01-1991
			HK	1007446 A1	09-04-1999
			JP	2836703 B2	14-12-1998
			JP	3136020 A	10-06-1991
			KR	171891 B1	20-03-1999
			US	5327273 A	05-07-1994
EP 0329153	A	23-08-1989	JP	1211552 A	24-08-1989
			JP	2558488 B2	27-11-1996
			JP	1254644 A	11-10-1989
			JP	2639385 B2	13-08-1997
			DE	68903229 D1	26-11-1992
			DE	68903229 T2	08-04-1993
			EP	0329153 A2	23-08-1989
			US	5324451 A	28-06-1994
EP 0309774	A	05-04-1989	CN	1032182 A	05-04-1989
			DE	3876059 D1	24-12-1992
			EP	0309774 A2	05-04-1989
			HK	44096 A	22-03-1996
			JP	1152430 A	14-06-1989
			JP	2532606 B2	11-09-1996
			KR	9700352 B1	08-01-1997

EPO FORM P0159

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 00 8128

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-06-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0309774	A		RU 2046390 C1	20-10-1995
			US 5676880 A	14-10-1997
			US 5770109 A	23-06-1998
			DD 282543 A5	12-09-1990
EP 0211646	A	25-02-1987	DE 3684967 D1	27-05-1992
			EP 0211646 A2	25-02-1987
			US 5114614 A	19-05-1992
			US 4780240 A	25-10-1988
			JP 2525153 B2	14-08-1996
			JP 63022893 A	30-01-1988
US 3977769	A	31-08-1976	JP 967959 C	31-08-1979
			JP 50153782 A	11-12-1975
			JP 53048196 B	27-12-1978
			JP 967960 C	31-08-1979
			JP 50155482 A	15-12-1975
			JP 53048197 B	27-12-1978
			FR 2275794 A1	16-01-1976
			GB 1508029 A	19-04-1978
EP 0994097	A	19-04-2000	EP 0994097 A2	19-04-2000
			JP 2000186064 A	04-07-2000
			US 6217954 B1	17-04-2001
EP 0937765	A	25-08-1999	EP 0937765 A1	25-08-1999
			JP 11310551 A	09-11-1999
			US 6128065 A	03-10-2000

EPO FORM P0189

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

